



Steel grade

Material No. / Werkstoff-Nr.	PREMIUM 1.2709 ESU
Description	X3NiCoMoTi18-9-5
BS	1.2709 ESR
AISI/SAE	1.2709 ESR
Search for alternatives in the ABRAMS STEEL GUIDE®	www.steel-guide.co.uk/alternatives/1.2709ESR

Specifications



Precision round steel with machining allowance [PRS/BA]
 peeled / rough-turned
 L: 500 mm
 L: 1,000 mm



Round steel [RS]
 black
 L: 500 mm
 L: 1,000 mm

Chemical composition BS 1.2709 ESR (reference value %)

C	Si	Mn	P	S	Cr	Mo	Ni	Ti	Co
0 – 0.03	0 – 0.1	0 – 0.15	0 – 0.01	0 – 0.1	0 – 0.25	4.5 – 5.2	17.0 – 19.0	0.8 – 1.2	8.5 – 10.0

Physical properties

Hardness (delivery condition)	max. 325 HB, tempered						
Tensile strength R _m (as received condition)	approx. 1100 N/mm ²						
Working hardness	max. 56 HRC						
Thermal expansion coefficient 10 ⁻⁶ m/(m • K)	20 - 100°C	20 - 200°C	20 - 300°C	20 - 350°C	20 - 400°C	20 - 450°C	20 - 500°C
	10.1	10.5	10.9	11.1	11.3	11.5	11.8
Thermal conductivity W/(m • K)	23°C	150°C	300°C	350°C	400°C	500°C	
	18.4	20.4	22.7	23.2	23.5	24.0	

Technical properties

Ultra-high strength tool steel with excellent toughness, high yield point and high tensile strength. Easy heat treatment at low temperatures. Good dimensional stability and low distortion. Good machinability when hardened.

Applications


Slides, gearing stamps, cold heading tools, embossing tools, press dies, hot press mould and tools, tool holders, cutting punches, die casting moulds (for light metal alloys), plastic moulds, reinforcements, light metal processing, shear knives, nozzles, distributor pins, cores.



Heat treatment

	Temperature	Cooling	Hardness
Soft annealing	850 - 1100°C	Furnace	max. 325 HB
Hardening	Temperature approx. 490°C	Quenching in Air	

Tempering diagram



ABRAMS PREMIUM STEEL

is a registered trademark of
 Abrams Engineering Services GmbH & Co. KG
 Hannoversche Str. 38 · 49084 Osnabrueck / Germany
 Managing Director: Dipl.-Wi.-Ing. Dr. Juergen Abrams

Amtsgericht Osnabrueck / Germany, HRA 6865
 VAT-No.: DE 221940667
 General Partner: Abrams Engineering Verwaltungs GmbH
 Amtsgericht Osnabrueck / Germany, HRB 20019

T: +44 (0) 121 368 0910
 F: +44 (0) 121 368 0911

sales@premium-steel.co.uk
 www.premium-steel.co.uk
 www.shop.premium-steel.co.uk
 www.steel-guide.co.uk

www.premium-steel.co.uk/news

